

CARBO CrMo 2 AC

International standards	Material No.	1.7384
	EN 1599	E CrMo2 R 12
	AWS A 5.5	E 9013-G

Approvals ---

Typical applications and characteristics AC-weldable CrMo alloy electrode for welding high-strength joints on tempered steels up to 1100 N/mm². Suitable for welding creep-resistant CrMo steels in boiler and piping system construction. Resistant to high temperatures up to 500°C. Non-ageing welding deposit, resistant to alkaline solutions, heat treatable and case- harden able. Preheating and post weld heat treatment of base materials to be carried out acc. to the steel manufacturer's instructions.

Operating temperature Room temperature up to + 500 °C

Base materials	1.7380	10CrMo9-10	1.7259	26CrMo7
	1.7375	12CrMo9-10	1.7273	24CrMo10
	1.7380	GS-12 CrMo 9 10	1.7276	10CrMo11
	1.7379	GS-18 CrMo 9 10	1.7281	16CrMo9-3
	1.8075	10CrSiMoV7		

Mechanical properties of all-weld metal
(typical values)

Tensile strength R _m N/mm ²	Yield strength R _{eL} N/mm ²	Elongation A ₅ %	Impact energy ISO-V J + 20°C
650	510	22	80

Weld metal analysis
(typical, wt %)

C	Si	Mn	Cr	Mo
0.05	0.6	1.0	2.3	1.0

Current = - ~ / 65 V

Welding positions PA, PB, PC, PD, PE, PF,

Rebaking 1 h, 350 °C + / - 10 °C (if necessary)

Dia./Length	Amperage (A)	Pcs./ packet	Pcs./ carton	kg / 1000	kg / packet	kg / carton
2.5 x 350	70 - 110	238	952	16,8	5.0	20.0
3.2 x 350	95 - 150	153	651	32,7	5.0	20.0
4.0 x 350	130 - 190	97	385	51,9	5.0	20.0
5.0 x 450	150 - 240	64	238	101,0	6.0	24.0

Rev. 000