

# CARBO 4519 HE

<b>International standards</b>	Material No.	1.4519
	EN 1600	E 20 25 5 Cu N L R 53
	AWS A 5.4	E385-17 /mod.

**Approvals** ---

**Typical applications and characteristics** CARBO 4519 HE is an electrode with an alloyed core wire and a recovery of 160% well suited for joint welding on the same or similar corrosion resistant CrNiMoCu steels along with low alloyed steels. Overlays with this electrode leave a pierce and tension resistant deposit that is also resistant to intergranular (IK) corrosion, specifically from acids and non-oxidating materials (i.e. sulfuric, phosphorous acids or ammonium acetate).

**Operating temperature** - 60° C up to + 400° C

<b>Base materials</b>	1.4339	GX32CrNi28-10	1.4536	GX 2 NiCrMoCuN 20-18
	1.4500	GX7NiCrMoCuNb25-20	1.4539	X 1 NiCrMoCu25-20-5
	1.4505	X4NiCrMoCuNb20-18-2	1.4585	GX7CrNiMoCuNb18-18
	1.4506	X5NiCrMoCuTi20-18	1.4586	X5NiCrMoCuNb22-18
	1.4531	GX2NiCrMoCuN20-18		

<b>Mechanical properties of all-weld metal</b> ( typical values )	<b>Tensile strength <math>R_m</math> N/mm<sup>2</sup></b>	<b>Yield strength <math>R_{p0,2}</math> N/mm<sup>2</sup></b>	<b>Elongation <math>A_5</math> %</b>	<b>Impact strength ISO – V J at – 40° C</b>
	580	380	40	80

<b>Weld metal analysis</b> (typical, wt %)	<b>C</b>	<b>Si</b>	<b>Mn</b>	<b>Cr</b>	<b>Ni</b>	<b>Mo</b>	<b>Cu</b>
	0,02	0,8	1	20	25	4,5	1,5

**Current** = + / ~ , 50 V

**Welding positions** PA, PB

**Rebaking** 1 h, 350° C + / - 10° C ( if necessary )

Dia./Length	Amperage (A)	Pcs./packet	Pcs./carton	kg/1000	kg/packet	kg/carton
2,0 x 300	40 - 55	238	952	16,8	4,0	16,0
2,5 x 300	60 - 80	131	525	30,5	4,0	16,0
3,2 x 350	80 – 110	97	388	51,6	5,0	20,0
4,0 x 350	115 - 140	64	256	78,2	5,0	20,0
5,0 x 450	130 - 180	38	153	157,0	6,0	24,0

Statements on composition and application are just for the applier's information. Statements on mechanical properties always refer to the all-weld-metal according to valid standards. Carbo-Weld may change the characteristics of its products without notice. We recommend the applier to check our products for their special application autonomously.

Rev. 000

Statements on composition and application are just for the applier's information. Statements on mechanical properties always refer to the all-weld-metal according to valid standards. Carbo-Weld may change the characteristics of its products without notice. We recommend the applier to check our products for their special application autonomously.