

CARBO 4820 MPR

International standards	Material No.	1.4820
	EN 1600	E 25 4 R 52
	DIN 8556	E 25 4 MP R 23

Approvals --

Typical applications and characteristics

CARBO 4820 MPR is an AC-weldable electrode with a recovery of 140% for fabrication-welding on equal or similar, corrosion and heat-resistant steels and steel-castings. The weld-deposit is on equal base-material scale-resistant and, by reason of its low nickel-content, resistant against attack of sulphurous gases at higher temperatures up to 1150°C. When welding CARBO 4820 AC low heat-input should be guaranteed as alloys of such chemistry are sensitive to embrittlement at 600-800°C. The interlayer-temperature must not exceed 300°C.

Operating temperature From room temperature up to + 1150° C

Base materials	1.4340	GX40CrNi27-4	1.4745	GX40CrSi23
	1.4710	GX30CrSi6	1.4746	X8CrTi25
	1.4711	X10CrSi6	1.4762	X10CrAl24
	1.4722	X10CrSi13	1.4776	GX40 CrSi29
	1.4723	X10 CrAl13	1.4821	X20CrNiSi25-4
	1.4740	GX40CrSi17	1.4822	GX40CrNi24-5
	1.4741	X2CrAlTi18-2	1.4823	GX40CrNiSi27-4
	1.4742	X10CrAl18		

Mechanical properties of all-weld metal (typical values)

Tensile strength R_m N/mm ²	Yield strength $R_{p0,2}$ N/mm ²	Elongation A_5 %	hardness HB
700	500	20	Ca. 180

Weld metal analysis (typical, wt %)

C	Si	Mn	Cr	Ni
0,06	1,0	0,7	25	4,7

Current = + / ~ / 50 V

Welding positions PA, PB, PC, PD, PE, PF

Rebaking 1 h, 350° C + / - 10° C (if necessary)

Dia./Length	Amperage (A)	Pcs./packet	Pcs./carton	kg/1000	kg/packet	kg/carton
2,5 x 350	70 - 90	178	712	28,3	5,0	20,0
3,2 x 350	80 - 120	105	421	47,5	5,0	20,0
4,0 x 450	120 - 170	65	259	92,6	6,0	24,0
5,0 x 450	170 - 240	41	166	144,7	6,0	24,0

Rev. 000