

# CARBO 4842 AC

<b>International standards</b>	Material No.	1.4842
	EN 1600	E 25 20 R 12
	AWS A 5.4	E310-16

**Approvals** --

**Typical applications and characteristics**

CARBO 4842 AC is an AC-weldable rutile-coated electrode with an alloyed core, suitable for joining corrosion-proof, highly heat-proof and non-scaling CrNi-steels which are subject to service temperatures up to 1200° C.

The electrode is also suitable for joint welding Cr-, CrSi-, and CrAl steels and for cladding low alloy base metals. The weld metal alloy is highly hot-crack-proof.

Keep temperature as low as possible during welding.

Annealing to 250°C and post-weld tempering to 700°C is required on ferritic base materials.

The electrode is mainly used in furnace-construction, for fittings and pipelines.

**Operating temperature** From room temperature up to + 1200° C

<b>Base materials</b>	1.4710	GX30CrSi6	1.4832	GX 25CrNiSi20-14
	1.4713	X10CrAl7	1.4841	X15CrNiSi25-20
	1.4762	X10CrAl24	1.4845	X12CrNi25-21
	1.4825	GX25CrNiSi18-9	1.4846	GX40 CrNiSi25-21
	1.4826	GX40CrNiSi22-9	1.4848	GX40CrNiSi25-20
	1.4828	X15CrNiSi20-12		

**Mechanical properties of all-weld metal ( typical values )**

Tensile strength $R_m$ N/mm <sup>2</sup>	Yield strength $R_{p0,2}$ N/mm <sup>2</sup>	Elongation $A_5$ %	Impact strength ISO – V J at room temperature
600	350	30	80

**Weld metal analysis (typical, wt %)**

C	Si	Mn	Cr	Ni
0,10	0,6	3	25	21

**Current** = + / ~ / 50 V

**Welding positions** PA, PB, PC, PD, PE, PF

**Rebaking** 1 h, 300° C + / - 10° C ( if necessary)

Dia./Length	Amperage (A)	Pcs./packet	Pcs./carton	kg/1000	kg/packet	kg/carton
2,5 x 300	50 - 75	219	874	18,3	4,0	16,0
3,2 x 350	75 - 110	138	552	36,2	5,0	20,0
4,0 x 350	100 - 145	91	365	54,8	5,0	20,0
5,0 x 450	120 - 165	54	218	110,1	6,0	24,0

Rev. 000

Statements on composition and application are just for the applier's information. Statements on mechanical properties always refer to the all-weld-metal according to valid standards. Carbo-Weld may change the characteristics of its products without notice. We recommend the applier to check our products for their special application autonomously.